

Disclaimer: This article has been published immediately upon acceptance (by the Editors of the journal) as a provisional PDF from the revised version submitted by the authors(s). The final PDF version of this article will be available from the journal URL shortly after approval of the proofs by authors(s) and publisher.

Improving Composite Resin Performance Through Decreasing its Viscosity by Different Methods

Kusai Baroudi and Rasha Said Mahmoud The Open Dentistry Journal, Volume 9, 2015

ISSN: 1874-2106 DOI: 10.2174/1874210620150601E001

Article Type: Review Article

 Received:
 February 15, 2015

 Revised:
 April 25, 2015

 Accepted:
 April 27, 2015

Provisional PDF Publication Date: June 08, 2015

© Baroudi and Mahmoud; Licensee Bentham Open.

This is an open access article licensed under the terms of the Creative Commons Attribution Non-Commercial License (http://creativecommons.org/licenses/ by-nc/3.0/) which permits unrestricted, non-commercial use, distribution and reproduction in any medium, provided the work is properly cited.

Improving Composite Resin Performance Through Decreasing its Viscosity by Different Methods

Kusai Baroudi and Rasha Said Mahmoud

Department of restorative dental sciences, Al-Farabi college, Riyadh, Saudi Arabia.

Running title: Improving Composite Properties by Decreasing Viscosity

Correspondence address:

Kusai Baroudi

Department of restorative dental sciences

Al-Farabi College. Riyadh 11691, P.O.Box 85184, Kingdom of Saudi Arabia

Business Tel: 00966-12273151 - Fax: +966 1 2324580 - E-mail: d kusai@yahoo.co.uk

Abstract

The aim of this work was to present the different current methods of decreasing viscosity of resin composite materials such as (using flowable composites, lowering the viscosity of the monomer mixture, heating composites and applying sonic vibration) and furnish dentists with a basis that can provide criteria for choosing one or another to suit their therapeutic requirements. The four discussed methods proved that lowering composite viscosity improves its handling and facilitates its application to cavities with complicated forms, decreasing time for procedure and improving marginal adaptation. Other properties improved by decreasing composite resin viscosity were controversial between the four methods and affected by other factors such as composite brand and light cure unit.

Keywords: Resin composite, low viscosity, improving properties.

Introduction

In the last decade, growing demands by patients for mercury-free, esthetic restorations has markedly increased the use of direct, light-activated resin composites in restorative dentistry. [1]

A major drawback of current composite-based resins is that they contract or shrink during conversion from monomer to polymer. The resin matrix of all composite- based resin restorative materials shrinks volumetrically approximately 10 percent during polymerization. [2] This polymerization shrinkage stresses the adhesive between the tooth and the restorative material, frequently resulting in failure of this bond and marginal infiltration. [3]

These problems have activated producers to find solutions and to make either the material or the technique easier to apply and faster to use. The effect of lowering viscosity to improve adaptation of the composite and to improve ease of placement has been shown to be important.[4]

Compared with conventional composite resins, these new composite resins with low viscosity boast few advantages: easily applicable to cavities with complicated forms, time required for the filling procedure is short, and excellent in cavity sealing. [5, 6]

1-Flowable composites

One of the methods used for decreasing composite viscosity is the development of flowable resin composites. Flowable resin composites; being less viscous material improve the wettability by flowing onto all prepared surfaces creating an intimate union with the micro structural defects in the floor and the walls of the cavity preparation. Also, act as a flexible intermediate layer that help

to relieve stresses during polymerization shrinkage of the restorative resin. These characteristics and a syringe delivery system make them an ideal choice for the use as a liner. [7, 8] Flowable composites achieve their lower viscosity primarily by a reduction in reinforcing filler content and changes in the matrix chemistry. [9, 10] However, it is well known that a decrease in filler content will affect various properties of a hardened composite resin, such as the mechanical strength and curing shrinkage. [11] Against this background, it is important to investigate how to lower the viscosity of a composite resin without decreasing its filler content. [12] Thus far, the most uncomplicated method of decreasing the viscosity of composites is to lower the viscosity of the monomer mixture itself.

2-Lowering monomer viscosity

The base monomer most widely used commercially is BisGMA (bisphenol A diglycidil dimethacrylate; MW=512 g/mol. Despite its high intrinsic reactivity, the presence of hydroxyl groups on the backbone and the π - π interactions given by the aromatic rings increase the initial viscosity (η =1,200 Pa) to a point that the homopolymer typically does not reach high conversion.[13] For that reason, and also to improve handling characteristics and allow incorporation of higher inorganic filler contents, BisGMA is usually combined with low free viscosity monomers like TEGDMA (triethylene glycol dimethacrylate; MW=286 g/mol, η =0.01 Pa. However, addition of TEGDMA increases water sorption and polymerization shrinkage.[14, 15] To overcome these effects, studies have been directed toward developing low viscosity, more hydrophobic Bis-GMA analogs such as the hydroxyl-free propoxylated Bis-GMA (CH3Bis-GMA) and propoxylated fluorinated Bis-GMA (CF3Bis-GMA), as replacements for TEGDMA in Bis-GMA mixtures.[16, 17] Also, in an attempt to improve properties of methacrylate resins,

aldehyde-propanal (propionaldehyde) or diketone-diacetyl (2,3-butanedione) have been added as potential crosslinking agents with appreciable success. [18, 19]

3-Heating composite

Many polymer resins exhibit lower viscosity when they are heated. The theoretical basis for this behavior is that thermal energy forces the composite monomers or oligomers further apart, allowing them to slide by each other more readily. Studies have shown that heating general polymers and resin composites lowers viscosity and thereby improves adaptation. [20]

4-Sonic vibration

A new method of restoration relies on more sophisticated instruments that condense the material by vibration. Such devices have been created by several producers and operate according to the same principle: sonic vibration .The principle of this technique assumes that vibration lowers the viscosity of the resin, allowing the material to flow and easily adapt to the cavity walls without air pores, in a similar way as a flowable composite. Thus, a condensable material with increased viscosity can be used similarly to a flowable composite, without the disadvantage of high polymerization shrinkage and poor mechanical properties. [21]

Our review aimed to disclose if decreasing viscosity of resin composites through the four mentioned methods has an impact on the performance of the restoration by improving its properties.

Materials and methods

With the help of currently available literature, this paper attempted to point out four methods used for decreasing composite viscosity and their ability to improve its properties. The electronic database PubMed was searched for scientific articles on the four methods. The search was carried out between 2004 and 2014 to represent the latest developments at the last 10 years.

The search words low viscosity, flowable composite, low viscosity monomers, preheated composites and sonic vibration were used. The search was done for each method separately. Total 59 papers were selected out of 70 papers. The selection was done on the basis of papers that correlate the selected method of decreasing viscosity to its effect on the performance of restoration. The rejected papers were discussing other aspects which not related to the scope of the review. The results of selected studies were presented in Tables 1, 2, 3, and 4. The papers were listed in the tables with ascending arrangement according to the year of publication.

Table	1:	Studies	that	investigated	micro	leakage	and	marginal	adaptation	of	flowable
compos	sites	5.									

First author +	Site of resin	Tested variables	Conclusion
year	application		
Olmez A ^[22] 2004	Class II composite restorations with the margins below the cemento-enamel junction as a liner	Marginal microleakage and internal voids	The use of flowable resin composites provided a reduction in marginal microleakage and a reduction in some parts of the internal voids or total voids
Tredwin, C.J ^[23] 2004	Class II cavities as aliner	Micro leakage	Leakage data do not support the use of flowable resin composite linings in Class II resin composite restorations
Lindberg A[24] 2005	Class II resin composite restorations as a liner	Interfacial adaptation	Neither the use of flowable resin composite liner nor the curing used influenced the interfacial adaptation
Loguercio, A. D ^[25] 2005	Class V as a liner	Clinical performance over 1 year	The use of Filtek Flow as a liner under Filtek Z250 restorations did not improve the clinical performance of class V restorations after 6 and 12 months of evaluation.

Efes BG, ^[26] 2006	Occlusal cavity as a liner	Two –year clinical performance	The clinical performance of occlusal restorations did not benefit from the additional use of the flowable composite.
Celik C ¹ 27] 2007	Non-carious cervical lesions.	Two-year clinical performance	Different types of resin materials demonstrated acceptable clinical performance in non-carious cervical lesions.
Sadeghi M ^[28] 2009	Class II as gingival liner	Micro leakage	The groups utilizing flowable liners had significantly less microleakage with no significant difference between utilizing flowable composite or flowable compomer
Kubo S ^[29] 2010	Non-carious cervical lesions	Three-year clinical performance	There were no significant differences in the clinical performances between the hybrid and the flowable composite for each variable acceptable clinical performance up to 3 years.
Gallo JR [[] ^{30]} 2010	Occlusal as a restoration	Clinical efficacy	Marginal discoloration and marginal adaptation significantly worsened at 36 months.
Van dijken J ^W ^[31] 2011	Class II restorations as a liner	Long term clinical performance	The use of flowable resin composite as an intermediate layer did not result in improved effectiveness of the Class II restorations
Simi, B ^[32] 2011	Class II as a liner	Micro leakage	Both resin-modified and flowable composite liners under nanocomposite restorations result in comparable reduction of microleakage.
Bonilla E D ^[33] 2012.	Minimally invasive occlusal restorations.	Micro leakage	Using flowable composite in minimally invasive occlusal restorations might result in undue restoration pitting or degradation.
Arslan S ^[34] 2013	Class V restorations as intermediate material	Micro leakage	Micro leakage is not affected by the application of either conventional or new-generation flowable composite resin as an intermediate material between composite resin and dental substrates
Pecie R ^[35] 2013	Class II as a liner	Marginal adaptation	The application of flowable composite as a liner may not improve marginal adaptation and is product dependent.

First author	Monomer change	Variables tested	Result
+ Year			
	Replace TEGDMA	Mechanical	The analogue CH3 Bis-GMA, which
Pereira SG	in Bis-GMA	properties	allows the preparation of medium-
2005	mixture with either		viscosity resins, is a good candidate
2005	CF3 Bis-GMA		mixtures materials with CH3 Bis-
	CI'S DIS-OWIA		GMA diluents showed an enhanced
			microhardness
OKAMURA	Experimental	Mechanical and	Mechanical (i.e., compressive,
H ^[37]	composite resins of	physical	diametral tensile, and bending)
	low-viscosity	properties	strength of a polymer obtained from
2006	monomer mixtures		one new monomer mixture without
	of newly developed		fillers was similar to that of a bis-
	polyfunctional		GMA/TEGDMA (2/1 weight ratio)
	acrylates		based polymer.
			In terms of setting shrinkage, the
			composites consisting of new
			monomer mixtures exhibited
			significantly smaller snrinkage than the big CMA based compositor, and
			decreased with increase in filler
			content
Charton, C	co-monomer bis-	Shrinkage stresses	The viscosities of the UEDMA bases
[38]	GMA /TEGDMA	~8	were exactly the same as those of the
	(70/30 and 50/50 %		bis-GMA ones.
2007	and co-monomer		Shrinkage stress Statistically, there
	UEDMA/TEGDMA		was a negative correlation between
	(88.5/11.5 and		viscosity, Tg and shrinkage stress.
	66.5/33.5 %)		
D 111 A	Combining bis-	Wear, roughness	The findings correlate with additives
Prakki , A [39]	GMA and	and hardness	ability to improve degree of
2008	TEGDMA, CH(3)bis GMA or		composites/conclumers thereby
2008	CF(3)bis-GMA		enhancing mechanical properties
	with aldehyde or		Bis-GMA/TEGDMA and bis-
	diketone		GMA/CH(3)bis-GMA copolymers
			with additives became smoother after
			abrasion test.
Prakki A,	Two additives,	Mechanical	The ability of additives to improve
[40]	aldehyde or	properties	degree of conversion of some
2009	diketone, to Bis-		composite systems thereby enhancing
	GMA-based		mechanical properties.

Table 2: Studies that investigated the decreasing viscosity through monomer changes.

	composites containing TEGDMA, (CH ₃ Bis-GMA) or (CF ₃ Bis-GMA).		
Denis, A. B [41] 2012	Bis-GMA diluted with CH3bis-GMA containing 0, 2, 8, 16 and 24 mol% propionaldehyde	Physical, rheological, and mechanical properties	24 mol% of Propionaldehyde significantly increased comonomer degree of conversion; Increased %DC is known to improve resin mechanical properties such as surface hardness
Prakki A ^[42] 2012	Additives of Bis-GMA based copolymers andthat of TEGDMA, CH3Bis-GMA or CF3Bis-GMA.	Water sorption characteristics	Aldehyde and diketone led to increases in the water sorption characteristics of experimental resins.

Table 3: Studies that investigated the effect of preheating resin composites on micro leakage in class II and V, degree of conversion, mechanical properties, polymerization shrinkage, hardness and marginal adaptation.

First author	Temperature	Variables tested	Results
+ year			
Aksu, M. N ^[43] (2004).	130°C	Micro leakage in Class II composite	Preheating of the composite investigated resulted in significantly less micro leakage at the cervical margin compared to the control or the use of the corresponding flowable resin.
Darnoch M ^[44] 2005	Between 3°C and 60 °C	Monomer conversion and duration of light exposure	Pre-heating composite prior to photoactivation provides greater conversion requiring reduced light exposure than with room- temperature composite.
Wagner WC ¹ 2008	54.4°C	Micro leakage in Class II composite restorations	Preheating the composite resulted in significantly less micro leakage at the cervical margins compared to the flowable liner and control.
Walter R ^[46] 2009	37°C, 54°C, or 68°C	Polymerization shrinkage	Preheating composite to relatively high temperatures (54°C or 68°C) to increase its flow and adaptation causes an increase in volumetric shrinkage
Lohbauer U ^[47] 2009	Between 10°C. and 68 °C.	Degree of conversion	Pre-heating of resin composites does not increase degree of conversion over time. Polymerization shrinkage as a function of pre- heating temperatures exhibited a linear correlation after 5 min, but no statistically different behavior after 24 h.
Lucey S ^[48] 2010	60 °C	Pre-cured viscosity and post-cured surface hardness	Pre-heating resin composite reduces its pre-cured viscosity and enhances its subsequent surface hardness.
Fróes-Salgado, N. R ^[49] (2010)	68 °C	Marginal adaptation (MA), degree of conversion (DC), flexural strength (FS), and polymer cross-	The pre-heated composite showed better MA than the room-temperature groups. Composite pre-heating and energy density did not affect the DC, FS and PCL .

		linking (PCL)	
Tantbirojn, D ^[50] 2011	68°C	Hardness and postgel shrinkage	Preheating of the composites only slightly increased hardness values and did not negatively affect postgel shrinkage.
Deb,S ^[51] 2011	22 °C and 60 °C.	Flow and marginal adaptation	Pre-warming of the composites studied enhanced flow as observed by measuring film thickness and did not significantly affect other properties.
Dos Santos, R. A ^[52] 2011	23°C, 54°C and 60°C	Micro leakage in Class II cavities restored with dental composite	Preheating the resin composite did not improve the micro leakage means when high-irradiance LED was used; however, it decreased the micro leakage means when a QTH with low irradiance was used.
Nada, K ^[53] 2011	37°C and 54°C	Mechanical properties	Pre warming significantly improved surface hardness and bulk properties of the composites; however, this improvement was significant in only some of the tested materials.
Karaarslan, E. S ^[54] (2012	37°C,54°C and 68°C	Micro leakage in Class V cavities	No significant differences among the preheated groups.

Table 4: Studies that investigated the effect of sonic vibration on depth of cure, marginal micro leakage, and mechanical performance.

First author	Vibration device	Variables tested	Conclusion
+ Year			
Yapp R ^[55] 2011	Sonic fill	Depth of cure of several composite restorative materials	Sonicfill is adequately cured at the maximum recommended depth when cured with the Demi curing light
Eunice, C ^{[56}] 2012	SonicFillTM (Kerr/Kavo	Marginal micro leakage in class v	SonicFill TM only has the advantage of better clinical handling, reducing labour time no influence in con- cerning microleakage
http://www.ncbi.nlm.nih.gov /pubmed?term=Draenert M%5BAuthor%5D&cauthor= true&cauthor_uid=23570302 Ilie, N ^[57] 2013	SonicFill, Kerr;	Mechanical performance of seven bulk-fill RBCs	The significant highest flexural strengths were measured for SonicFill
http://www.ncbi.nlm.nih.gov /pubmed/?term=Poggio C%5Bauth%5D Poggio, C [[] 58] 2013	SonicFill (Kerr)	microleakage in "deep" Class II composite restorations with gingival cavosurface margin below the CEJ	Significant prevalence of Score 0 (no dye penetration) was reported both for Groups 4 (SonicFill) and 5 (Grandio),
Alrahlah, A ^{[59}] 2014	SonicFill™.	Depth of cure of bulk fill resin composites through using Vickers hardness profiles (VHN).	SonicFill exhibited the highest VHN SonicFill and Tetric EvoCeram Bulk Fill had the greatest depth of cure among the composites examined.

Discussion

Today, improvements in formulations, optimization of properties and the development of new techniques for placement have made the restoration of direct composite more reliable and predictable. Producers tried to decrease the viscosity of dental composite to make either the material or the technique easier to apply and faster to use. Several solutions have been proposed to decrease composite viscosity.

Flowable composites

The first way discussed in this review was; using flowable composite table (1) .[22-35] The use of flowable resin composite as an intermediate layer liner when studied for occlusal, cervical and proximal restorations, showed different results. Some authors found this application improves the marginal seal, Olmez *et al.*, 2004 [22] concluded that; a composite lining in a Class II resin composite with margins below the cemento enamel junction may reduce marginal microleakage and voids in the interface and the total number of voids in the restoration. Sadeghi *et al.*, 2009 [28] also concluded that; a layer of flowable materials at the gingival floor of Class II composite restorations may be recommended to improve the marginal seal of a restoration. The same idea was supported by Simi *et al.*, 2011 [32] who concluded that; both resin-modified and flowable composite liners under nano composite restorations result in comparable reduction of micro leakage.

In contrast; others failed to show any benefits from using flowable composite as a liner. Tredwin *et al.*, 2004 [23] found use of a flowable composite liner against cementum/dentin was associated with increased micro leakage. Lindberg *et al.*, 2005 [24] and Pecie *et al.*, 2013 [35] found that the use of flowable resin composite did not rinfluence the interfacial adaptation. Van dijken *et*

al., 2011 [31] also concluded that; the use of flowable resin composite as an intermediate layer did not result in improved effectiveness of the Class II restorations.

Using liner under occlusal restoration was studied by Efes *et al.*, 2006 [26] who found that; the clinical performance of occlusal restorations did not benefit from the additional use of the flowable composite.

Using flowable composite as a liner in class V cavities was studied by Arslan *et al.*, 2013 [34] who stated that; micro leakage is not affected by the application of either conventional or newgeneration flowable composite resin as an intermediate material between composite resin and dental substrates. Also, Loguercio *et al.*, 2005 [25] stated that; the use of Filtek Flow as a liner under Filtek Z250 restorations did not improve the clinical performance of class V restorations after 6 and 12 months of evaluation.

When performance of flowable resin materials in non-carious cervical lesions was studied; acceptable clinical performance (except for the retention rates of the Dyract Flow restorations) in non-carious cervical lesions was stated by Celik *et al.*, 2007 [27] with no significant differences were found between the flowable and microhybrid resin materials (p > 0.05). The same conclusion was recorded by Kubo *et al.*, 2010 [29] who found that: both types of resin flowable and hybrid resin composite in conjunction with S3 Bond demonstrated an acceptable clinical performance up to 3 years when applied to non-carious cervical lesions with no significant differences.

Clinical efficacy of two flowable composite resins used to restore occlusal caries lesions was investigated by Gallo *et al.*, 2010 [30] who observed that marginal discoloration, polishability and marginal adaptation significantly worsened at 36 months and he suggested that they should

be limited to small restorations such as preventive resin restorations having isthmus widths of one-quarter or less of intercuspal distance. Bonilla *et al.*, 2012 [33] reached the same conclusion when they studied placing flowable composite as minimally invasive occlusal restorations. Their results showed that a conventional microhybrid composite material, leaked significantly less than all the flowable composite groups. Tiny microscopic bubbles were seen within many of the flowable composite specimens, as were a few voids.

Lowering monomer viscosity

The second discussed way for decreasing composite resin viscosity was decreasing monomer mixture viscosity (table 2) [36-42]. Most of the composite resins widely used in restorative dentistry contain the highly viscous monomer 2,2-bis [4-(2-hydroxy-3-methacryloxyprop-1-oxy) phenyl]propane (Bis-GMA) and low-viscosity monomers, used as diluents, in order to achieve high filler loading. In particular, triethylene glycol dimethacrylate (TEGDMA) has been extensively used for such purpose.

Studies have been directed toward developing low viscosity, hydroxyl free, more hydrophobic Bis-GMA analogs. Okamura *et al.*, 2006 [37] evaluated the dental application possibility of producing, experimental composite resins of low-viscosity monomer mixtures using low-viscosity monomer mixtures of newly developed polyfunctional acrylates. The viscosity of composite pastes with high filler content was markedly lower than that of Bis-GMA based composites. Compressive strengths of composite resins produced using the new monomer mixture. In terms of setting shrinkage, the composites consisting of new monomer mixtures exhibited significantly smaller shrinkage than the Bis-GMA based composites, and decreased with increase

in filler content. Such small setting shrinkage might be attributed to the relatively large volume of polyfunctional monomers and the relatively small intermolecular distance.

Pereira *et al.*, 2005 ^[36] investigated the influence of new diluent agents, diluent ratio and filler content, on relevant mechanical properties of several novel composite resins containing Bis-GMA as resin matrices, and to compare these with the properties of composites based on TEGDMA, a conventionally used diluent. Two Bis-GMA analogues were synthesized combining three monomer mixtures (Bis-GMA/TEGDMA, Bis-GMA/CH3 Bis-GMA and Bis-GMA/CF3 Bis-GMA). Materials with CH3 Bis-GMA showed an enhanced micro hardness VHN. Mean Flexural strength (FS) was higher for matrices containing TEGDMA. Overall, dilution favored FS and VHN but not modulus of elasticity ME.

Adding additives to the Bis-GMA monomer that decreased viscosity was studied by Prakki *et al.*, 2009 [40] where two additives, propionaldehyde/aldehyde or 2,3-butanedione/diketone, was added. Degree of conversion (DC %), flexural strength (FS), modulus of elasticity (E), modulus of resilience (R) and diametral tensile strength (DTS) were determined. Incorporation of additives led to an increase in DC%, FS and E for Bis-GMA/TEGDMA and Bis-GMA/CH (3) Bis-GMA systems. R-values for all systems were unaffected by addition of additives. They had no significant effect on DC% or mechanical properties of Bis-GMA/CF (3) Bis-GMA. Same conclusion reached by the same authors [39] when they tested wear, roughness and hardness as affected by the two additives and concluded that; incorporation of additives led to improved W and H values for bis-GMA/TEGDMA and Bis-GMA/CF₃bis-GMA, also concluded that; Bis-GMA/TEGDMA, bis-GMA/CH₃bis-GMA copolymers with additives became smoother after abrasion test.

The same conclusions was reached by Denis *et al.*, 2012 [41] who evaluated the physical, rheological, and mechanical properties of Bis-GMA diluted with CH3bis-GMA containing 0, 2, 8, 16 and 24 mol% propionaldehyde. It has been reported that the viscosity of propionaldehyde is $3 \times 10-5$ Pa.s and its incorporation into comonomers significantly lowers the viscosity of CH3bis-GMA-based resins. The present findings revealed that the incorporation of propionaldehyde into the experimental resins gradually increased % DC as the mol % of the additive increased.

Prakki *et al.*, 2012 [42] tested the effect of additives on the water sorption characteristics of Bis-GMA based copolymers and composites containing TEGDMA, CH3Bis-GMA or CF3Bis-GMA. Water sorption and desorption were evaluated in a desorption-sorption-desorption cycle. Water uptake (%WU), water desorption (%WD), equilibrium solubility (ES; µg/mm³), swelling (f) and volume increase (%V) were calculated using appropriate equations. All resins with additives had increased %WU and ES. TEGDMA-containing systems presented higher %WU, %WD, ES, f and %V values, followed by resins based on CH3Bis-GMA and CF3Bis-GMA. Aldehyde and diketone led to increases in the water sorption characteristics of experimental resins.

Charton *et al.*, 2007 [38] showed different results about monomer viscosity when he investigated Influence of glass transition temperature Tg, viscosity and chemical structure of monomers on shrinkage stress in light-cured dimethacrylate-based dental resins. The large differences in stress values for the pairs with the same viscosity, showed that; it is not the viscosity in itself which has a dominating influence on stresses (via the DC). They concluded that; whatever the viscosity, the UEDMA-based matrices developed higher shrinkage stresses than the Bis-GMA homologues.

Heating composite

The third discussed method in this review was preheating composite before photo activation (table 3) [43-54]. Chair side warming of composite resins before photo polymerization is one of the recent trends in their application.

Daronch *et al.*, 2005 ^[44] concluded that; pre-heating composite prior to photo activation provides greater conversion requiring reduced light exposure than with room-temperature composite. Different results were reached by Lohbauer *et al.*, 2009 [47] and Fróes-Salgado *et al.*, 2010. [49]

The first one concluded that; pre-heating of resin composites does not increase degree of conversion over time. It can be clinically beneficial, due to a superior marginal adaptation. The second one reached the same conclusion when he studied the effect of composite pre-polymerization temperature and energy density on the marginal adaptation (MA), degree of conversion (DC), flexural strength (FS), and polymer cross-linking (PCL) of a resin composite. He concluded that: Pre-heating the composite prior to light polymerization did not alter the mechanical properties and monomer conversion of the composite, but provided enhanced composite adaptation to cavity walls.

Deb *et al.*, 2011 [51] evaluated if pre warming of composites would influence the flow and enhance marginal adaptation and, he stated that; pre-warming of the composites studied enhanced flow as observed by measuring film thickness and did not significantly affect other properties.

Micro leakage as affected by preheating was discussed with two different points of view. The first one correlated composite preheating to the reduction in micro leakage in class II composite. Wagner *et al.*, 2008 45 and Aksu *et al.*, 2004 [43] supported this view, the first one compared

micro leakage in Class II composite restorations prepared using: preheated resin composite, and unheated composite and found no statistical differences among materials at the occlusal margin. However, at the cervical margin, the preheated samples showed statistically lower micro leakage than the controls and all other treatments. The second study also stated that; preheating of the composite investigated resulted in significantly less micro leakage at the cervical margin compared to the control or the use of the corresponding flowable resin. The other point of view by Dos Santos *et al.*, 2011 [52] who found that; the decrease in micro leakage in Class II cavities restored with preheated dental composite happened when a QTH with low irradiance was used but, not improved when high-irradiance LED was used. Karaarslan *et al.*, 2012 [54] also tested the micro leakage as affected by preheating composite and found no significant differences among the preheated groups.

Mechanical properties and polymerization shrinkage for preheated composite were tested with varied results. Walter *et al.*, 2009 [46] studied whether temperature affects the polymerization shrinkage of composite resin and concluded that: Preheating composite to relatively high temperature 54c or 88 c to increase its flow and adaptation causes an increase in volumetric shrinkage. This result was opposed by Tantbirojn *et al.*, 2011 [50] who evaluated the effect of composite preheating and light-curing duration on hardness and postgel shrinkage and stated that; preheating of the composites only slightly increased hardness values and did not negatively affect postgel shrinkage.

Lucey *et al.*, 2010 [48] tested the pre-cured viscosity and post-cured surface hardness for the preheated composite and stated that; pre-heating resin composite reduces its pre-cured viscosity and enhances its subsequent surface hardness. This conclusion was supported by Nada *et al.*, 2011 [53] who found that the effect of pre polymerization warming on composites' mechanical

properties, is material dependent; pre warming significantly improved surface hardness and bulk properties of the composites; however, this improvement was significant in only some of the tested materials.

Sonic vibration

The last discussed method was sonic vibration (table 4) [55-59]. Up to now, little independent studies assessed the vibration technique, also some data offered by the producers of such devices being available.

Microleakage was investigated by two studies the first by Eunice *et al.*, 2012 [56] who stated that; the sonic system has no effect concerning microleakage. The second study by Poggio *et al.*, 2013 [58] on contrast proved that sonic fill composites showed the lowest microleakage values when compared with other groups tested micro leakage in "deep" Class II composite restorations with gingival cavosurface margin below the CEJ.

Alrahlah *et al.*, 2014 [59] studied post-cure depth of cure of bulk fill resin composites through using Vickers hardness profiles (VHN), they stated that SonicFill exhibited the highest VHN, also sonic fill and Tetric EvoCeram bulk fill had the greatest depth of cure among the composites examined. Ilie *et al.*, 2013 [57] also studied the mechanical performance of seven bulk-fill RBCs and he stated that; the significant highest flexural strengths were measured for SonicFill.

Yapp *et al.*, 2011 [55] found that ;sonic fill adequately cured at the maximum recommended depth when cured with Demi curing light set to yield a saw tooth when used according to manufacturer's direction for use.

Conclusions

No benefits from the additional use of the flowable composite as a liner for interfacial adaptation and micro leakage. Lowering monomer viscosity by replacing TEGDMA in Bis-GMA/diluent mixtures with CH3 Bis-GMA, or CF3 Bis-GMA consequently improves degree of conversion DC, polymerization shrinkage (PS) and handling properties. Additives are able to improve degree of conversion of some composite systems thereby enhancing mechanical properties. Preheating composite reduces viscosity and increases flowability, which facilitates better adaptation to cavity walls; this reduces micro leakage and results in superior marginal adaptation. Condensation of composite resins can be faster achieved by using vibrating instruments. Vibration decreases the viscosity of the material and facilitates its flow within the preparation irregularities with better adaptation of the material to the cavity walls.

References

- Ilie N, Jelen E, Clementino-Luedemann T, Hickel R. Low shrinkage composite for dental application. Dent Mater 2007; 26:149-55.
- [2] Van Meerbeek B, Perdigao J, Lambrechts P, Vanherle G. The clinical performance of adhesives. J Dent 1998; 26:1-20.
- [3] Browne RM, Tobias RS. Microbial microleakage and pulpal inflammation: a review. Endod Dent Traumatol 1986; 2:177-83.
- [4] Clelland NL, Pagnotto MP, Kerby RE, Seghi RR. Relative wear of flowable and highly filled composite. J Prosthet Dent 2005; 93:153-7.
- [5] Yazici AR, Ozgunaltay G, Dayangac B. The effect of different types of flowable restorative resins on microleakage of Class V cavities. Oper Dent 2003; 28:773-8.

- [6] Neme AM, Maxson BB, Pink FE, Aksu MN. Microleakage of Class II packable resin composites lined with flowables: An *in vitro* study. Oper Dent 2002; 27:600-5.
- [7] Payne JH, The marginal seal of Class II restorations: Flowable composite resin compared to injectable glass ionomer. J Clin Pediatr Dent 1999; 23:123-30.
- [8] Unlu N, Krakaya S, Ozer F, Say EC. Reducing microleakage in composite resin restorations: An *in vitro* study. Eur J Prostho Rest Dent 2003; 11:171-5.
- [9] Bayne SC, Thompson J Y, Swift Jr, E J, Stamatiades P, Wilkerson M. A characterization of first-generation flowable composites. J Am Dent Assoc 1998; 129: 567-77.
- [10] Baroudi K, Silikas N, Watts DC. Edge-strength of flowable resin-composites. J Dent 2008; 36: 63-8.
- [11] Miyasaka T, Okamura H. Measurement of polymerization shrinkage of composite resin using laser displacement meter. J Dent Mater 2005; 24: p. 385.
- [12] Miyasaka T, Yoshida T. Synthesis and some properties of novel low viscous base monomer. J Dent Mater 2000; 19: p.177.
- [13] Peutzfeldt A. Resin composites in dentistry: the monomer systems. Eur J Oral Sci 1997; 105: 97-116.
- [14] Anseth KS, Newman SM, Bowman CN. Polymeric dental composites: properties and reaction behavior of multimethacrylate dental restorations. Adv Polym Sci 1995; 122:177-217.
- [15] Braden M. The formulation of composite filling materials. Oper Dent 1978; 3:97-102.
- [16] Kalachandra S. Dimethacrylate monomers and polymers as biomaterials. Polym Sci 1997; 2:95-106.

- [17] Pereira SG, Nunes TG, Kalachandra S. Low viscosity dimethacrylate comonomer compositions [Bis-GMA and CH3Bis-GMA] for novel dental composites; analysis of the network by stray-field MRI, solid state NMR and DSC & FTIR. Biomater 2002; 23: 3799-806.
- [18] Peutzfeldt A. Quantity of remaining double bonds of diacetyl-containing resins. J Dent Res 1994; 73:511-5.
- [19] Peutzfeldt A, Asmussen E. Influence of ketones on selected mechanical properties of resin composites. J Dent Res 1992; 71:1847-50.
- [20] Blalock JS, Holmes RG, Rueggeberg FA. Effect of temperature on unpolymerized composite resin film thickness. J Prosthet Dent 2006; 96:424-32.
- [21] Iovan G, Stoleriu S, Moldovanu A, Morogai S, Andrian S. SEM study of the interface between the cavity wall and composite resin in cavities filled using vibration. Int J Med Dent 2011; 1: 254-8.
- [22] Olmez A,OztasN,Bodur H. The effect of flowable resin composite on microleakage and internal voids in class II composite restorations. Oper Dent 2004; 29:230-35.
- [23] Tredwin CJ, Stokes A, Moles DR. Influence of flowable liner and margin location on microleakage of conventional and packable Class II resin composites. Oper Dent 2004; 30:32-8.
- [24] Lindberg A, van Dijken JW, Horstedt P. *In vivo* interfacial adaptation of class II resin composite restorations with-and without a flowable resin composite liner. Clin Oral Investig 2005; 9:77-83.

- [25] Loguercio AD, Zago C, Leal K, Ribeiro NR, Reis A. One-year clinical evaluation of a flowable resin liner associated with a microhybrid resin in noncarious cervical lesions. Clin oral investig 2005; 9:18-20.
- [26] Efes BG, Dörter C, Gömec Y, Koray F. Two-year clinical evaluation of ormocer and nanofill composite with and without a flowable liner. J Adhe Dent 2006; 8:119-26.
- [27] Celik C, Ozgunaltay G, Attar N. Clinical evaluation of flowable resins in noncarious cervical lesions: two-year results. Oper Dent 2007; 32:313-21.
- [28] Sadeghi M. Influence of flowable materials on microleakage of nanofilled and hybrid Class II composite restorations with LED and QTH LCUs. Indian J Dent Res 2009; 20:159-63.
- [29] Kubo S, Yokota H, Yokota H, Hayashi Y, Three-year clinical evaluation of a flowable and a hybrid resin composite in non-carious cervical lesions. J Dent 2010; 38:191-200.
- [30] Gallo JR, Burgess JO, Ripps AH, Walker RS, Maltezos MB, Mercante DE, Davidson JM. Three-year clinical evaluation of two flowable composites. Quintessence Int 2010; 41:497-503.
- [31] Van Djken J W, Pallesen U. Clinical performance of a hybrid resin composite with and without an intermediate layer of flowable resin composite. A 7-year evaluation. Dent Mater J 2011; 27:150-6.
- [32] Simi B, Suprabha B S. Evaluation of microleakage in posterior nanocomposite restorations with adhesive liners. JCD 2011; 14: p.178.

- [33] Bonilla E D, Stevenson R G, CaputoA A, White SN. Microleakage Resistance of Minimally Invasive Class I Flowable Composite Restorations. Oper Dent 2012; 37: 290-8.
- [34] Arslan S, Demirbuga S, Ustun Y, Dincer AN, Canakci BC, Zorba YO. The effect of a new-generation flowablecomposite resin on microleakage in Class V composite restorations as an intermediate layer. J Conserv Dent 2013; 16:189-93.
- [35] Pecie R, Onisor I, Krejci I, Bortolotto T. Marginal Adaptation of Direct Class IIComposite Restorations with Different Cavity Liners. Oper Dent 2013; 38: 210-20.
- [36] Pereira SG, Osorio R, Toledano M and Nunes TG. Evaluation of two Bis-GMA analogues as potential monomer diluents to improve the mechanical properties of light polymerized composite resins. Dent Mater 2005; 21: 823-30.
- [37] Okamura H, Miyasaka T, Hagiwara T. Development of Dental Composite ResinUtilizing Low-shrinking and Low-viscous Monomers. Den Mater J 2006; 25: 437-44.
- [38] Charton C, Falk V, Marchal P, Pla F, Colon P. Influence of Tg, viscosity and chemical structure of monomers on shrinkage stress in light-cured dimethacrylate-based dental resins. Dent Mater J 2007; 23:1447-59.
- [39] Prakki A, Cilli R, Mondelli RFL, Kalachandra S. *In vitro* wear, surface roughness and hardness of propanal-containing and diacetyl-containing novel composites and copolymers based on bis-GMA analogs. Dent Mater 2008; 24: 410- 17.
- [40] Prakki A, Pereira PNR and Kalachandra S. Effect of propionaldehyde and 2, 3butanedione additives on the mechanical properties of Bis-GMA analog-based composites. Dent Mater 2009; 25: 26-32.

- [41] Denis AB, Plepis AMG, Martins VDCA, Pereira JC, Cilli R, Prakki A. Properties of experimental resins based on synthesized propoxylated bis-GMA with different propionaldehyde ratios. Mater Res 2012; 15: 397-402.
- [42] Prakki A, Cilli R, Vieira IM, Dudumas K, Pereira JC. Water sorption of CH3-and CF3-Bis-GMA based resins with additives. J Applied Oral Sci 2012; 20:472-77.
- [43] Aksu MN, LINGER J. Effect of pre-heating composite on microleakage in Class II restorations. J Dent Res 2004:83.
- [44] Daronch M, Rueggeberg FA, De Goes MF. Monomer Conversion of Pre-heated Composite. J Dent Res 2005; 84: 663-67.
- [45] Wagner WC, Asku MN, Neme AL, Linger J B, Pink FE, Walker S. Effect of Preheating Resin Composite on Restoration Microleakage. Oper Dent 2008; 25: 3087-97.
- [46] Walter R, Swift Jr EJ, Sheikh H, Ferracane JL. Effects of temperature on composite resin shrinkage. Quintessence Int 2009; 40.
- [47] Lohbauer U, Zinelis S, Rahiotis C, Petschelt A, Eliades G. The effect of resin composite pre-heating on monomer conversion and polymerization shrinkage. Dent Mater 2009; 25: 514-9.
- [48] Lucey S, Lynch CD, Ray NJ, Burke FM, Hannigan A. Effect of pre-heating on the viscosity and microhardness of a resin composite. J Oral Rehabil 2010; 37(4): 278-82.
- [49] Fróes-Salgado NR, Silva LM, Kawano Y, Francci C, Reis A, Loguercio AD. Composite pre-heating: effects on marginal adaptation, degree of conversion and mechanical properties. Dent Mater 2010; 26: 908-14.
- [50] Tantbirojn D, Chongvisal S, Augustson DG, Versluis A. Hardness and postgel shrinkage of preheated composites. Quintessence Int 2011; 51-9.

- [51] Deb S, Di Silvio L, Mackler HE, Millar BJ. Pre-warming of dental composites. Dent Mater 2011; 27: 51-9.
- [52] Dos Santos RA, Lima AF, Soares GP, Ambrosano GMB, Marchi GM, Lovadino JR, Aguiar FHB. Effect of preheating resin composite and light-curing units on the microleakage of Class II restorations submitted to thermocycling. Oper Dent 2011; 36: 60-5.
- [53] Nada K, El-Mowafy O. Effect of precuring warming on mechanical properties of restorative composites. Int J Dent 2011; 2011: 536212.
- [54] Karaarslan ES, Usumez A, Ozturk B, Cebe MA. Effect of cavity preparation techniques and different preheating procedures on microleakage of class V resin restorations. Eur J Dent 2012; 6: 87-94.
- [55] Yapp R, Powers JM. Depth of cure of several composite restorative materials. Dent Advis Res Report 2011; 33:1.
- [56] Eunice C, Margarida A, João C L, Filomena B, Anabela P, Pedro A, Marques F
 M. 99m Tc in the evaluation of microleakage of composite resin restorations with Sonic
 fill. An *in vitro* experimental model. Open J Stomatol 2012; 2: 340-47.
- [57] Ilie N, Bucuta S, Draenert M Bulk-fill resin-based composites: an *in vitro* assessment of their mechanical performance. Oper Dent 2013; 38: 618-25.
- [58] Poggio C, Chiesa M, Scribante A, Mekler J, Colombo M. Microleakage in Class II composite restorations with margins below the CEJ: *In vitro* evaluation of different restorative techniques. Med Oral Patol Oral Cir Bucal 2013; 18: 793-98.
- [59] Alrahlah A, Silikas N, Watts DC. Post-cure depth of cure of bulk fills dental resin-composites. Dent Mater 2014; 30: 149-54.